

<p>1999-374625/32 A96 D22 F04 NISY 1997.11.07  NIPPON SYNTHETIC CHEM IND CO *JP 11140761-A  1997.11.07 1997-322313(+1997JP-322313) (1999.05.25) D04H 1/54,  1/72  <b>Hot water soluble non-woven fabric manufacturing method -  involves melt spinning hot water soluble resin from nozzle cavity,  useful for medical application</b>  <b>C1999-111031</b></p>	<p>A(11-B15B, 12-S5G, 12-S5L, 12-V3) D(9-C6) F(1-  C8B, 2-C1, 4-E4)</p>
<p>Hot water soluble non-woven fabric manufacturing method comprises  a hot water soluble resin from a nozzle cavity is subjected to melt  spinning. Gas is sprayed from an injection pore, installed near the  nozzle cavity and the fiber formed is collected.</p> <p><u>USE</u>  The method is used for medical application.</p> <p><u>ADVANTAGE</u>  The disposable non-woven fabric having hot water solubility and  water resistance is obtained and environmental problems are  prevented.  (4pp3123DwgNo.0/0)</p>	<p>JP 11140761-A</p>